

PERFILES LAMINADOS

IPE

Especificaciones Generales

Calidad	ASTM A36
Otras calidades	Previa Consulta
Largo normal	6.00m y 12.00m
Otros largos	Previa Consulta
Acabado	Natural
Otro acabado	Previa Consulta



DENOMINACION	DIMENSIONES					SECCION		PESOS		TIPOS			
	h	s	g	t	R	cm ²	kg/mt	I _x	I _y	W _x	W _y		
	mm	mm	mm	mm	mm								
IPE 80	80	46	3.80	5.20	5	7.64	6.00	80	8.49	20.00	3.69		
IPE 100	100	55	4.10	5.70	5	10.30	8.10	171	15.90	34.20	5.79		
IPE 120	120	64	4.40	6.30	5	13.20	10.40	318	27.70	53.00	8.65		
IPE 140	140	73	4.70	6.90	7	16.40	12.90	541	44.90	77.30	12.30		
IPE 160	160	82	5.00	7.40	7	20.10	15.80	869	68.30	109.00	16.70		
IPE 180	180	91	5.30	8.00	7	23.90	18.80	1320	101.00	140.00	22.20		
IPE 200	200	100	5.60	8.50	9	28.50	22.40	1940	142.00	194.00	28.50		
IPE 220	220	110	5.90	9.20	9	33.40	26.20	2770	205.00	252.00	37.30		
IPE 240	240	120	6.20	9.80	12	39.10	30.70	3890	284.00	324.00	47.30		
IPE 270	270	135	6.60	10.20	12	45.90	36.10	5790	420.00	429.00	62.20		
IPE 300	300	150	7.10	10.70	15	53.80	42.20	8360	604.00	557.00	80.50		
IPE 330	330	160	7.50	11.50	15	62.60	49.10	11770	788.00	713.00	98.50		
IPE 360	360	170	8.00	12.70	118	72.70	57.10	16270	1040.00	904.00	123.00		
IPE 400	400	180	8.60	13.50	118	84.50	63.30	23130	1320.00	1160.00	146.00		
IPE 450	450	190	9.40	14.60	21	98.80	77.70	33740	1680.00	1500.00	176.00		
IPE 500	500	200	10.20	16.00	21	116.00	90.70	48200	2140.00	1930.00	214.00		
IPE 550	550	210	11.10	17.20	24	134.00	106.00	67120	2670.00	2440.00	254.00		

